



TECHNICAL DATASHEET

One-component polyurethane foam Subfloor Adhesive Gunfoam

One-component, ready to use polyurethane foam adhesive for gluing construction blocks in non-load bearing interior walls.

Main benefits

- Faster work compared to using mortar
- Foam gun is the only tool needed
- Dust free work environment

Fields of application

Foam adhesive can be used for gluing construction blocks in non-bearing interior walls. Consult a sales agent, a dealer or an architect regarding compatibility with various stone-based materials and other technical issues.

Application instruction

Application temperature

Air temperature during use: 23°F to +95°F. Best results starting from +41°F. Test the sufficiency of adhesion at the place of application if using below +41°F.

Can temperature during application: +41°F to +77°F, best results at +68°F.

Foam can has to be warmed with water or air (max. +86°F) before starting work in low temperatures.

Surface preparation

Remove dust, loose particles and grease from the surfaces. Moisten dry substrate to ensure better results.

Application method

Shake the can vigorously at least 20 times. Hold the foam can in upright position, turn the gun to the can by holding the gun handle with one hand, and turn the can with the other hand. Make sure that the gun is not pointed at other persons when turning it. The can must not be screwed to the gun with the valve upside down or by turning the gun on the can. Turn the can upside down and start applying. The output of foam adhesive can be adjusted by the gun trigger.

Gluing of construction blocks

First row of blocks must be well leveled using mortar. Adhesive should be applied to both vertical and horizontal surfaces. Foam adhesive will form a thin glue layer. Press the stone surfaces together immediately after the adhesive has spread.

Cleaning

Uncured foam adhesive can be removed with acetone, cured foam adhesive with mechanical means.

Seal Spray Foam

5717 Salmen St
New Orleans, LA 70123
USA

Phone: 504-734-1315
Website: www.sealsprayfoam.com



Technical data

Properties	Value	Unit
Tack free time	5-10	min
Completely cured (73 °F)	<24	h
Completely cured (41/23 °F)	<72	h
Temperature resistance of cured foam adhesive	-58 ... +194	°F
Fire class of cured foam adhesive (DIN 4102-1)	B3	

The values specified were obtained at 73 °F and 50% relative humidity, unless otherwise specified. These values may vary depending on environmental factors such as temperature, moisture and type of substrates.

Storage and shelf-life

Guaranteed shelf life is 36 months from production date if stored in unopened packaging in a cool and dry place at +41°F to +86°F. The foam cans must not be stored above +122°F, nearby heat sources or in direct sunlight. Store and transport in a vertical position.

Limitations

The foam adhesive does not adhere to Teflon, polyethylene and silicon surfaces.

Safety regulations

Use only in well-ventilated areas. Do not smoke during application! Use protective gear when necessary. Keep out of the reach of children. See label and safety data sheet (SDS) for more information.

Seal Spray Foam

5717 Salmen St
New Orleans, LA 70123
USA

Phone: 504-734-1315
Website: www.sealsprayfoam.com

Version 2.1



Note: The instructions in the present documentation are based on tests carried out by the manufacturer and are presented in good faith. Due to variations in materials and substrates as well as the various application possibilities that are beyond our control, the manufacturer is not liable for the results achieved. In any case, it is recommended to test the product suitability at the place of application. Manufacturer reserves the right to modify products without prior notice.

Seal Spray Foam

5717 Salmen St
New Orleans, LA 70123
USA

Phone: 504-734-1315
Website: www.sealsprayfoam.com