



## TECHNICAL DATASHEET

# One-component polyurethane foam Window & Door Gunfoam

One-component, ready to use polyurethane gunfoam for various building applications, e.g. sealing of joints and penetrations, installation of window and door frames, thermal and acoustic insulating. High yield allows doing more work with one canister. Low curing pressure and moderate post expansion avoid deformation of building elements. Adheres well to most materials like wood, concrete, stone, plaster, metal, PVC and polystyrene.

### Main benefits

- High yield allows doing more work with one canister
- Suitable for use in higher temperatures, up to +104°F
- Low curing pressure and moderate post expansion avoid deformation of building elements
- High thermal and acoustic insulation value

### Fields of application

- Installation of window and door frames
- Sealing of thermal and acoustic insulation boards
- Insulation of penetrations
- Sealing and connection of joints
- Reducing the impact of thermal bridges

### Application instruction

#### Application temperature

Air temperature during use: +41°F to +104°F, best results at +68°F.

Can temperature during application: +41°F to +95°F, best results at +68°F.

#### Surface preparation

Remove dust, loose particles and grease from the surfaces. Moisten dry substrate to ensure better results. Protect adjacent surfaces with paper, plastic film or other suitable material.

#### Application method

Shake the can vigorously at least 20 times. Hold the foam can in upright position, turn the gun to the can by holding the gun handle with one hand, and turn the can with the other hand. Make sure that the gun is not pointed at other persons when turning it. The can must not be screwed to the gun with the valve upside down or by turning the gun on the can. Turn the can upside down and start applying. The foam output can be adjusted by the gun trigger.

When applying foam in layers moisten slightly between each layer.

#### Cleaning

Uncured foam can be removed with acetone, cured foam with mechanical means.

## Seal Spray Foam

5717 Salmen St

New Orleans, LA 70123

USA

Phone: 504-734-1315

Website: [www.sealsprayfoam.com](http://www.sealsprayfoam.com)



## Technical data

Properties	Value	Unit
Tack free time (TM 1014)	6-10	min
Cutting time (TM 1005)	<30	min
Completely cured in joint, 3x5cm (+23 °C)	<8	h
Curing pressure (TM 1009, moistened surfaces)	<2	kPa
Post expansion (TM 1010)	<80	%
Density in joint, 3x10cm (WGM106)	0.75-1	lb/ft <sup>3</sup>
Dimensional stability (TM 1004)	<2	%
Temperature resistance of cured foam	-58 ... +194	°F
Fire rating (exceeds ASTM E-84)	FSI/SDI	Flame Spread Index: 10 Smoke Development: 15
Tensile strength / elongation (TM 1018, dry surfaces)	>85 / 16	kPa / %
Tensile strength / elongation (TM 1018, moistened surfaces)	>95 / 13	kPa / %
Compression strength (TM 1011, moistened surfaces)	>25	kPa
Shear strength (TM 1012, moistened surfaces)	>35	kPa
Thermal conductivity (EN 12667, TM 1020)	0,033	W/(m·K)
Sound reduction index R <sub>st,w</sub> (EN ISO 10140)	62	dB
Water vapour permeability (EN 12086)	<0,06	mg/(m·h·Pa)
Foam yield in joint, 3x5 cm (WGM107), per 750 ml filling rate	20	m
Foam yield (TM 1003), per 750 ml filling rate	55	l

The values specified were obtained at 73 °F and 50% relative humidity, unless otherwise specified. These values may vary depending on environmental factors such as temperature, moisture and type of substrates.

Manufacturer uses test methods approved by FEICA designed to deliver transparent and reproducible test results, ensuring customers have an accurate representation of product performance. FEICA OCF test methods are available at: <http://www.feica.eu/our-industry/pu-foam-ocf.aspx>. FEICA is a multinational association representing the European adhesive and sealant industry, including one-component foam manufacturers. Further information at: [www.feica.eu](http://www.feica.eu).

## Storage and shelf-life

Guaranteed shelf life is 24 months from production date if stored in unopened packaging in a cool and dry place at +41°F to +86°F. The foam cans must not be stored above +122°F, nearby heat sources or in direct sunlight. Store and transport in a vertical position.

## Limitations

The foam does not adhere to Teflon, polyethylene and silicon surfaces. Cured foam is sensitive to UV-light and direct sunlight and therefore must be covered with suitable opaque sealant, filler, paint or other material.

## Seal Spray Foam

5717 Salmen St Phone: 504-734-1315  
 New Orleans, LA 70123 Website: [www.sealsprayfoam.com](http://www.sealsprayfoam.com)  
 USA

Version 3.1



## **Safety regulations**

Use only in well-ventilated areas. Do not smoke during application! Use protective gear when necessary. Keep out of the reach of children. See label and safety data sheet (SDS) for more information.

Note: The instructions in the present documentation are based on tests carried out by the manufacturer and are presented in good faith. Due to variations in materials and substrates as well as the various application possibilities that are beyond our control, the manufacturer is not liable for the results achieved. In any case, it is recommended to test the product suitability at the place of application. Manufacturer reserves the right to modify products without prior notice.

## **Seal Spray Foam**

5717 Salmen St  
New Orleans, LA 70123  
USA

Phone: 504-734-1315  
Website: [www.sealsprayfoam.com](http://www.sealsprayfoam.com)